



AFLAS®

GENERAL INFORMATION


WCR AFLAS® is a unique peroxide cured fluoroelastomer based upon an alternating copolymer of tetrafluoroethylene and propylene. It has excellent resistance to oil, strong acids and bases and a continuous service temperature of 230°C.

TYPICAL APPLICATIONS

- High temperature oil applications
- Resistance to strong Acids and Base including Sour Gas
- Not to be used in temperatures below -4 °C (25 °F)

TYPICAL PROPERTIES

- Hardness 80 Shore A
- Tensile Strength 14 MPa
- Elongation at break 200%
- Maximum continuous temperature: 230°C (446°F), with short term excursions to 260°C (500°F)



Notes: The greater distance from the middle, the better.
This is a general overview, in relation to other materials. For specific applications please contact WCR or WCR agents for advice.

MATERIAL DATA SHEET (MDS)

PRODUCT: WCR AFLAS® gaskets Edition 2018, Rev.1

1. IDENTIFICATION OF SUBSTANCE AND OF THE COMPANY

Issued by: Steve Cokonougher, WCR Incorporated, Washington C.H., Ohio 43160

Country: USA

Phone no: +1 (740) 333-3448

Fax no: +1 (740) 333-3452

E-mail address: scokonougher@wcrhx.com

Trade name: WCR AFLAS® Article numbers: 6th and 7th digit = 26 (x x x x 26)

Color Identification: Black rubber gasket with two green dots.

2. COMPOSITION/INFORMATION ON INGREDIENTS.

Composition: Peroxide cured Fluoroelastomer (copolymers of tetrafluoroethylene and propylene), carbon black, softener, curatives, and antioxidants and processing aids.

3. HAZARD IDENTIFICATION

General Information: Non-labeled product according to US/EU-regulations

Special attention should be paid to the following areas:

- * Particles can cause damage or irritation on the eye surface.
- * Sensitive persons can obtain skin irritation by unprotected handling of the product

4. FIRST-AID MEASURES

Emergency first aid procedures: Eye contact: Flush with water, consult physician. Skin contact: Wash with soap and water. Ingestion: As with swallowing any foreign substance, consult physician.

5. FIRE FIGHTING MEASURES

The material consists of organic raw materials known to be flammable.

In case of fire, follow the instructions given by appropriate firefighting authorities.

Flammable/Combustible: Yes, at very high temperatures far above 200°C, in presence of an ignition source.

Extinguishing Media: Water spray, high expansion foam or powder.

Special firefighting instructions: Treat as hydrocarbon fire.

Main hazardous combustion products: Carbon dioxide, carbon monoxide, nitrogen oxides, hydrocarbons (alcohols, aldehydes, ketones)

6. ACCIDENTAL RELEASE MEASURES

Waste disposal methods: Dispose of in accordance with local, state and federal regulations

7. HANDLING AND STORAGE

Treat as normal rubber products.

8. EXPOSURE CONTROLS/PERSONAL PROTECTION

Respiratory protection: Only when buffing or at temperatures above 100°C.

Protective gloves: Not normally required at normal use (unless person is especially sensitive to the product)

Eye protection: As required

Hygienic work practices: Industrial hygiene and safety practices should be observed.

9. PHYSICAL AND CHEMICAL PROPERTIES

Physical state: Solid

Odor: Very low

Appearance: Black material with two green dots

Specific gravity: 1.59-1.61 g/ml

Free monomers: Traces

Melting point: Not applicable

10. STABILITY AND REACTIVITY

Chemical stable: Yes

Hazardous polymerization: Will not occur

11. TOXICOLOGICAL INFORMATION:

Could cause skin irritation, or allergy, for some very sensitive persons.

12. ECOLOGICAL INFORMATION:

General Information: The products are very resistant to biodegradability, and not known to be eco-toxic.

13. DISPOSAL CONSIDERATIONS:

The products may be disposed as land filling, or be burned like other rubber or plastic products.

14. TRANSPORT INFORMATION:

No special precautions are necessary when transporting the product.

15. REGULATORY INFORMATION:

No labels are needed. See local and federal regulations.

16. OTHER INFORMATION:

The product is cured rubber. When exposed to higher temperatures, the lifetime of the product will decrease.